

## Jotamastic 80 MIO

### Product description

This is a two component polyamine cured epoxy mastic coating. It is a surface tolerant, micaceous iron oxide (MIO) pigmented, high solids product. Specially designed for areas where optimum surface preparation is not possible or desired. Can be used as primer, mid coat, finish coat or as single coat system in atmospheric and immersed environments. Suitable for properly prepared carbon steel and aged coating surfaces. It can be applied at sub zero surface temperatures.

### Typical use

General:  
Primarily designed for maintenance and repair.

Protective:  
Recommended for offshore environments, refineries, power plants, bridges, buildings, mining equipment and general structural steel.

### Other variants available

Jotamastic 80

Refer to separate TDS for each variant.

### Colours

grey, black

## Product data

Property	Test/Standard	Description
<b>STANDARD GRADE</b>		
Solids by volume	ISO 3233	79 ± 2 %
Gloss level (GU 60 °)	ISO 2813	semi gloss (35-70)
Flash point	ISO 3679 Method 1	35 °C
Density	calculated	1,62 kg/l
VOC-EU	IED (2010/75/EU) (calculated)	265 g/l
<b>WINTER GRADE</b>		
Solids by volume	ISO 3233	72 ± 2 %
Flash point	ISO 3679 Method 1	31 °C
Density	calculated	1,57 kg/l
VOC-EU	IED (2010/75/EU) (calculated)	293 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

All data is valid for mixed paint.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range STANDARD GRADE

Dry film thickness	75 - 200	µm
Wet film thickness	95 - 250	µm
Theoretical spreading rate	10,5 - 4	m <sup>2</sup> /l

### WINTER GRADE

Dry film thickness	75 - 200	µm
Wet film thickness	105 - 280	µm
Theoretical spreading rate	9,6 - 3,6	m <sup>2</sup> /l

## Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 2 (ISO 8501-1)	Sa 2 (ISO 8501-1)
Shop primed steel	Clean, dry and undamaged shop primer (ISO 12944-5 6.1)	Sa 2 (ISO 8501-1)
Coated surfaces	Clean, dry and undamaged compatible coating (ISO 12944-5 6.1)	Clean, dry and undamaged compatible coating (ISO 12944-5 6.1)

## Application

### Application methods

The product can be applied by

Spray:	Use airless spray.
Brush:	May be used. Care must be taken to achieve the specified dry film thickness.
Roller:	May be used. Care must be taken to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

#### STANDARD GRADE

Jotamastic 80 MIO Comp A	7 part(s)
Jotamastic 80 STD Comp B	1 part(s)

#### WINTER GRADE

Jotamastic 80 MIO Comp A	
--------------------------	--



## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	90 °C	90 °C
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat:	epoxy shop primer, inorganic zinc silicate shop primer, zinc epoxy, epoxy, epoxy mastic, inorganic zinc silicate
Subsequent coat:	polyurethane, epoxy, acrylic, vinyl epoxy

## Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotamastic 80 MIO Comp A	16	20
Jotamastic 80 STD Comp B	2.3	3
Jotamastic 80 Wintergrade Comp B	4	5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### Shelf life at 23 °C

Jotamastic 80 MIO Comp A	48 month(s)
Jotamastic 80 STD Comp B	48 month(s)
Jotamastic 80 Wintergrade Comp B	36 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

---

## Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

---

## Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---