

Jotafair

Product description

This is a two component solvent free epoxy fairing compound/filler. It has excellent application properties, high strength, good sandability and minimal shrinkage during cure. To be used as part of a complete coating system in atmospheric and immersed environments. Suitable for properly prepared carbon steel and composite surfaces.

Typical use

Apply by trowel or fairing board to smooth-out (fair) surface deflections on metal or composite substrates of yacht exteriors.

Colours

light green

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	100 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	100 °C
Density	calculated	0.7 kg/l

Region	Regulation	Test Standard	VOC Value
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	0 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	500 - 10000 µm
Wet film thickness	500 - 10000 µm
Theoretical spreading rate	2 - 0.1 m ² /l

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Application

Application methods

The product can be applied by

Trowel: Trowel on to achieve the required thickness and smoothness.

Product mixing ratio (by volume)

Jotafair Comp A 1 part(s)
Jotafair Comp. B 1 part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

Drying and Curing time

Substrate temperature	15 °C	23 °C	35 °C
Surface (touch) dry	12 h	8 h	4 h
Walk-on-dry	18 h	12 h	8 h
Dry to over coat, minimum	18 h	12 h	8 h
Dried/cured for service	10 d	7 d	5 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature **23 °C**

Pot life 20 min

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	120 °C
Immersed, sea water	50 °C	50 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy

Subsequent coat: epoxy

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotafair Comp A	1/4	3/5
Jotafair Comp. B	1/4	3/5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.