

## Megaprimer

### Product description

This is a two component, polyamide cured, high molecular weight epoxy coating. Designed as a sandable, high build, all purpose coating. Can be used as primer or sealer for fillers in atmospheric and immersed environments. Suitable for properly prepared carbon steel, aluminium, shop primed steel, composite and wooden substrates.

### Typical use

Exterior and interior areas, including hulls, above and below waterline, superstructures and decks. Suitable for osmosis prevention on composite hulls. To be used as a sealer on epoxy fillers and old polyurethane systems.

### Colours

grey, white

### Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	54 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	25 °C
Density	calculated	1.3 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	451 g/l
Hong Kong	Air Pollution Control (VOC) Regulation	Calculated	451 g/l
EU	European Paint Directive 2004/42/CE	Calculated	451 g/l
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	451 g/l
Korea	Korea Clean Air Conservation Act	Calculated	451 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

Dry film thickness	80 - 150 μm
Wet film thickness	150 - 280 μm
Theoretical spreading rate	6.8 - 3.6 m <sup>2</sup> /l

## Surface preparation

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 3 (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Aluminium	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface.	Abrasive blast cleaning to achieve a surface profile using non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Shop primed steel	Dry, clean and intact shop primer.	Sweep blasted or alternatively blasted to Sa 2 (ISO 8501-1) of at least 70 % of the surface.
Composite	Epoxy Composites should be free from any wax or mould release coating before starting any surface preparation. Random orbital sanding of the surfaces thoroughly to achieve an even profile by abrading the surface using P80-P120 grit aluminium oxide paper or silicon carbide sand papers. <b>NOTE:</b> For the coating of Unsaturated Polyester based composites, please contact your local Jotun office.	Epoxy Composites should be free from any wax or mould release coating before starting any surface preparation. Random orbital sanding of the surfaces thoroughly to achieve an even profile by abrading the surface using P80-P120 grit aluminium oxide paper or silicon carbide sand papers. <b>NOTE:</b> For the coating of Unsaturated Polyester based composites, please contact your local Jotun office.
Wood	Clean and dry surface. Surface contamination is to be removed by detergents and fresh water cleaning.	Clean and dry surface. Surface contamination is to be removed by detergents and fresh water cleaning.
Coated surfaces	New Jotun Yachting epoxy primer: Clean, dry and undamaged compatible coating Remove any contamination that could interfere with the intercoat adhesion.  Cured Jotun Yachting epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats,	New Jotun Yachting epoxy primer: Clean, dry and undamaged compatible coating Remove any contamination that could interfere with the intercoat adhesion.  Cured Jotun Yachting epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats,

	depending on condition. Fillers: Orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P100-P160.	depending on condition. Fillers: Orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P100-P160.
--	--	--

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

Jotun recommends no more than 2 steps of sandpaper grades when moving between grades.

## Application

### Application methods

The product can be applied by

Spray:	Use air spray or airless spray. Care must be taken to achieve the specified dry film thickness.
Brush:	Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
Roller:	May be used for small areas. Not recommended for first primer coat. Care must be taken to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Megaprimer Comp A	4 part(s)
Megaprimer Comp B	1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

### Guiding data for airless spray

Nozzle tip (inch/1000):	15-21
Pressure at nozzle (minimum):	150 bar/2100 psi

## Drying and Curing time

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	2 h	1 h	30 min
Walk-on-dry	14 h	6.5 h	3 h
Dry to over coat, minimum	8 h	4 h	3 h
Dried/cured for service	14 d	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and at the typical DFT for the product.

When product is diluted to help spraying with conventional spray equipment, it is required to allow to dry for 48 hours and dry sand the surface with P220/P320.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

**Paint temperature** 23 °C

Induction time 30 min  
Pot life 8 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	-
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, polyurethane  
Subsequent coat: epoxy, polyurethane

## Packaging (typical)

Volume (litres)	Size of containers (litres)
--------------------	--------------------------------

Megaprimer Comp A	4 / 16	5 / 20
Megaprimer Comp B	1 / 4	1 / 5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Shelf life at 23 °C

Megaprimer Comp A	24 month(s)
Megaprimer Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

## Disclaimer

# Technical Data Sheet

## Megaprimer



---

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---