

Solvalitt Midtherm Alu

Product description

This is a one component physically drying silicone acrylic coating. It is an aluminium pigmented product. It is heat resistant up to 260 °C. Can be used as primer, mid coat or finish coat in atmospheric environments. Suitable for properly prepared carbon steel, galvanised steel, stainless steel and aluminium substrates.

Typical use

Protective:

Designed as a heat resistant coating. Suitable for insulated and non insulated surfaces. Recommended as finish coat for insulated surfaces, in systems with suitable primers.

Other variants available

Solvalitt Midtherm

Refer to separate TDS for each variant.

Colours

aluminium

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	34 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	27 °C
Density	calculated	1 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	576 g/l
Hong Kong	Air Pollution Control (VOC) Regulation	Calculated	576 g/l
EU	European Paint Directive 2004/42/CE	Calculated	576 g/l
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	576 g/l
Korea	Korea Clean Air Conservation Act	KS M ISO 11890-1	568 g/l
China	GB 30981-2020 Limit of harmful substances of industrial protective coatings	GB/T 23985-2009 8.3	567 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.
Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	20 - 40	µm
Wet film thickness	60 - 120	µm
Theoretical spreading rate	17 - 8.5	m ² /l

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Stainless steel	The surface shall be sweep blast-cleaned with the nozzle angle at 45-60° from perpendicular at reduced nozzle pressure to create a sharp and angular surface profile using approved nonmetallic abrasive media.	The surface shall be sweep blast-cleaned with the nozzle angle at 45-60° from perpendicular at reduced nozzle pressure to create a sharp and angular surface profile using approved nonmetallic abrasive media.
Aluminium	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface.	Dry abrasive blast cleaning to SSPC-SP 13/NACE No. 6.
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	Sweep blast-cleaning using non-metallic abrasive leaving a clean, rough and even pattern.
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Application

Application methods

The product can be applied by

Spray: Use air spray or airless spray.

Brush: Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

Product mixing

Single pack

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 7 / Jotun Thinner No. 10

Guiding data for airless spray

Nozzle tip (inch/1000): 15-17

Pressure at nozzle (minimum): 100 bar/1450 psi

Drying and Curing time

Substrate temperature	5 °C	10 °C	23 °C	40 °C
Surface (touch) dry	45 min	30 min	15 min	10 min
Walk-on-dry	4 h	3 h	2 h	1 h
Dry to over coat, minimum	6 h	3 h	2 h	1 h

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Freshly applied Solvalitt film may have slightly reduced mechanical properties. This effect can however be overcome by heating the paint system to 200 °C for approx. 1 hour.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	260 °C	-

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, zinc silicate, silicone acrylic
Subsequent coat: silicone acrylic

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Solvalitt Midtherm Alu	5	5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Solvalitt Midtherm Alu 24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifouling may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
