

Jotatop AY20 WF

Product description

This is a one component waterborne acrylic emulsion coating. It is a versatile, fast drying product for exterior use. It has a glossy finish with very good gloss retention. It has good chemical resistance. Dries down to 41 °F (5 °C). To be used as topcoat in atmospheric environments. It is part of a complete waterborne system with a recommended Jotun waterborne primer or as a part of a hybrid system with suitable solvent borne primer.

Typical use

Protective:

Suitable for a wide range of industrial structures and industrial steel to be exposed to corrosive environments. Recommended for infrastructure and construction equipment.

Approvals and certificates

Contributes to satisfying the following credit(s):

- Indoor Environmental Quality (IEQ) under LEED® 2009

Fully complies with HJ2537-2014 requirements for VOC limit in Anticorrosive coatings

Additional certificates and approvals may be available on request.

Colors

According to colour card and Multicolor WF tinting system

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	36 ± 2 %
Gloss level (GU 60 °)	ISO 2813	gloss (70-85)
Density	calculated	1.2 kg/l

Region	Regulation	Test Standard	VOC Value
--------	------------	---------------	-----------

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	1.2 mils (30 µm)	2.4 mils (60 µm)
Wet film thickness	3 mils (85 µm)	7 mils (170 µm)
Theoretical spreading rate	490 ft ² /gal (12 m ² /l)	240 ft ² /gal (6 m ² /l)

Bright colors may need film thickness in the high end of the recommended specification range to achieve opacity.

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Application

Application methods

The product can be applied by

Spray:	Use air spray or airless spray.
Brush:	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller:	Use a suitable roller. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Product mixing

Single pack

Thinner/Cleaning solvent

Thinner: Fresh water

Guiding data for airless spray

Nozzle tip (inch/1000): 13-17
Pressure at nozzle (minimum): 150 bar/2100 psi

Guiding data for air spray

Nozzle tip: Pressure pot: 1.2-2.0 (mm)
Pressure at nozzle (minimum): Pressure pot: 2.1 bar/30 psi

Drying and Curing time

Substrate temperature	41 °F	50 °F	73 °F	104 °F
Surface (touch) dry	1h	45min	20 min	10min
Walk-on-dry	6h	3h	1h	1h
Dried to over coat, minimum	8h	4h	1.5h	1h

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	80 °C	-

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: acrylic

Additional information

Procedure for preparation and cleaning of application equipment

To avoid solvent contamination of the waterborne paint the spraying equipment has to be conditioned before use. All equipment containing solvents in the pump, hoses and gun have to be thoroughly cleaned according to the following instructions.

If the application equipment is made in stainless steel, designed for and only used for application of waterborne coatings this preparation and cleaning procedure is not needed.

Before spraying:

Circulate Jotun Thinner No. 17 through the equipment and hoses. Then Jotun Thinner No. 4 before fresh clean water.

After spraying:

Clean the equipment and hoses with water and alkaline detergent, then circulate Jotun Thinner No. 4 and finally Jotun Thinner No. 17.

Packaging (typical)

	Volume (liters)	Size of containers (liters)
Jotatop AY20 WF	20	20

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Protect from freezing at all times during storage and transport.

Recommended storage temperature is between 41 °F (5 °C) and 95 °F (35 °C).

Shelf life at 73°F (23 °C)

Jotatop AY20 WF 18 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifouling may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.