

## Jotapipe IL 426

### Product description

This is a two component polyamine cured phenolic/novolac epoxy coating. It is a specially designed internal pipe coating for aggressive service. It has a high resistance to most sour crude oils and a wide range of chemicals and solvents. It has outstanding chemical resistance to crude oil at temperatures up to 160 °C. To be used as single coat system only.

### Typical use

To be used as a high build internal lining for pipelines carrying hot sour crude, sour oil or gas as well as other aggressive media. The coating offers very good high temperature resistance.

### Colours

off-white

### Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	70 ± 2 %
Flash point	ISO 3679 Method 1	28 °C
Density	calculated	1.57 kg/l

The provided data is typical for factory produced products, subject to slight variation depending on colour. All data is valid for mixed paint.

### Film thickness per coat

Exact film thickness requirements will be determined by the client/project specification.

### Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1)	Sa 2½ (ISO 8501-1)
	Surface profile 35-50 µm, grade Fine G (ISO 8503-2)	Surface profile 35-50 µm, grade Fine G (ISO 8503-2)

## Application

### Application methods

The product can be applied by

Spray: Use airless spray.

### Product mixing ratio (by volume)

Jotapipe IL 426 Comp A 4 part(s)  
Jotapipe IL 426 Comp B 1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 23

### Guiding data for airless spray

Nozzle tip (inch/1000): 17-21  
Pressure at nozzle (minimum): 150 bar/2100 psi

## Drying and Curing time

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	16 h	4 h	2 h
Dry to handle	24 h	7 h	3 h
Dried/cured for service	14 d	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and at the typical DFT for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Dry to handle: Minimum time before the coated objects can be handled without physical damage.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Paint temperature 23 °C

Induction time 15 min  
Pot life 2 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	200 °C	200 °C

Heat resistant up to 160 °C. Applies to crude oil.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotapipe IL 426 Comp A	200 / 16	200 / 20
Jotapipe IL 426 Comp B	200 / 4	200 / 5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### Shelf life at 23 °C

Jotapipe IL 426 Comp A 12 month(s)  
Jotapipe IL 426 Comp B 12 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

---

## Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

---

## Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---