

## Jotashield ColourXtreme Silk (I)

### Product description

#### Type

This product is a superior quality, exterior, 100% pure acrylic water based topcoat.

#### Features and benefits

The unique heat reflective features and UV protected colours offer outstanding protection against heat from Infrared (IR) rays and destructive effect of UV rays present in Sunlight. It is a low-VOC, eco-friendly product that contributes to reducing energy consumption in cooling the interiors of buildings. Its unique formulation protects concrete from carbonation. The special acrylic binder provides durable and long lasting silk finish with low dirt pick up. Resistant to algae and fungus.

#### Recommended use

Ideal for decorating and protecting exterior surfaces and specially suits as a maintenance product.

#### Substrate

Cement plaster, concrete, block work, rendered surfaces etc.

### Product data

<b>Packaging size</b>	1 L, 4 L and 20 L		
<b>Colours</b>	Refer to Jotashield exterior colour card.		
<b>Gloss level</b>	6 - 8	EN ISO 2813 (60°)	
<b>Solids</b>	38	± 2	volume% Theoretical
<b>Specific gravity</b>	1,27	kg/l	Only for whites
<b>VOC</b>	13	g/l	ISO 11890 EU

### Application data

#### The product can be applied by

Spray : Use airless spray or conventional spray.

Roller : Recommended.

Brush : Recommended.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.53-0.69 mm (0.021-0.027")
<b>Spray angle degrees</b>	65-80°

#### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Recommended film thickness per coat

<b>Dry</b>	Minimum	27 µm
<b>Dry</b>	Maximum	38 µm
<b>Dry</b>	Typical	36 µm
<b>Wet</b>	Minimum	65 µm
<b>Wet</b>	Maximum	92 µm
<b>Wet</b>	Typical	80 µm

Film thickness will vary and are calculated as an average.

### Spreading rate per coat

<b>Theoretical</b>	Minimum	10 m <sup>2</sup> /l
<b>Theoretical</b>	Maximum	14 m <sup>2</sup> /l
<b>Theoretical</b>	Typical	10,25 m <sup>2</sup> /l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

### Thinner

Water

### Dilution

Maximum 10 %

### Cleaning of painting tools

Water

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

<b>Relative Humidity (RH)</b>	50 %	50 %	50 %
<b>Substrate temperature</b>	10 °C	23 °C	40 °C
<b>Surface (touch) dry</b>	12 h	6 h	2 h
<b>Hard dry</b>	16 h	8 h	4 h
<b>Dried to over coat, minimum</b>	12 h	6 h	2 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of foam release agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

#### Primer

# Technical Data Sheet

## Jotashield ColourXtreme Silk (I)



Jotashield Alkali Resistant Primer (I) or Jotashield Penetrating Primer : 1 Coat

### Topcoat

Jotashield ColourLast Silk (I) : 2 Coats

### Remarks

Other systems may be specified, depending on area of use.

Masking tape has to be removed immediately after application of the topcoat.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

This product is available in: India

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health- and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.