

## Chemtech GM

### Product description

This is a two component solvent free polyamine cured epoxy coating. Specially designed to be used as a lining in storage tanks in combination with glass fibre mats. Can be used as primer, mid coat or finish coat in atmospheric and immersed environments. Suitable for properly prepared carbon steel substrates only.

### Typical use

Specially designed for tank for the lining of the lower parts of storage tanks as secondary containment membrane. Suitable for maintenance and major repair.

### Colors

clear, white

### Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	100 %
Gloss level (GU 60 °)	ISO 2813	gloss (70-85)
Density	calculated	0.8 kg/l

  

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	0.94 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

Dry film thickness	39 mils (1000 µm)	118 mils (3000 µm)
Wet film thickness	39 mils (1000 µm)	118 mils (3000 µm)
Theoretical spreading rate	40 ft <sup>2</sup> /gal (1 m <sup>2</sup> /l)	10 ft <sup>2</sup> /gal (0.33 m <sup>2</sup> /l)

## Surface preparation

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Cleanliness corresponding to Sa 2½ (ISO 8501-1), Surface profile Medium to Coarse G (ISO 8503-2) or NACE No. 2 / SSPC SP-10, Surface profile 60-110 µm	Cleanliness corresponding to Sa 2½ (ISO 8501-1), Surface profile Medium to Coarse G (ISO 8503-2) or NACE No. 2 / SSPC SP-10, Surface profile 60-110 µm

## Application

### Application methods

The product can be applied by

See Application Guide.

### Product mixing ratio (by volume)

Chemtech GM Comp A	2.5 part(s)
Chemtech GM Comp B	1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17 / Jotun Thinner No. 23

### Guiding data for airless spray

Nozzle tip (inch/1000): 25-31

Pressure at nozzle (minimum): 200 bar/2900 psi

## Drying and Curing time

Substrate temperature	50 °F	73 °F	104 °F
Surface (touch) dry	14 h	7 h	5 h
Walk-on-dry	26 h	12 h	7 h
Dried to over coat, minimum	26 h	12 h	7 h
Dried/cured for service	14 d	7 d	3 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Paint temperature	73 °F
Pot life	30 min

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	120 °C
Immersed, sea water	70 °C	70 °C

Further resistance information can be found in Protective Product Resistance List available on Jotun's website, or contact your local Jotun office.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy  
Subsequent coat: epoxy

Tankguard Holding Primer can be used as a temporary protection and is fully compatible with the tank coating system.

## Packaging (typical)

	Volume (liters)	Size of containers (liters)
Chemtech GM Comp A	10	20
Chemtech GM Comp B	4	5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Shelf life at 73°F (23 °C)

Chemtech GM Comp A	24 month(s)
Chemtech GM Comp B	24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

---

## Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---