

Imprimación Multiuso Al Disolvente

Product description

Type

This product is an alkali resistant, solvent based primer. Based on alkyd resin.

Features and benefits

Contains Zinc phosphate as active corrosion preventing pigments. Resistant against dry heat up to 120°C. Quick dry.

Recommended use

Ideal as primer for steel and aluminium structures where a fast-drying primer is required. It can be used as a sealer primer for wood.

Product data

Packaging size	0.75 L and 4 L
Colours	White, grey and red
Solids by volume	44 ± 2 volume%

Application data

The product can be applied by

Roller : Recommended.

Brush : Recommended.

Spray : Use airless spray or conventional spray.

Guiding data for airless spray

Nozzle tip	0.015–0.021"
Spray angle degrees	40° - 80°
Pressure at nozzle	140 - 190 kg/cm ² (2100 psi)

Film thickness per coat

Typical recommended range

Dry film thickness	40 - 60 μm
Wet film thickness	90 - 135 μm

Film thickness will vary and are calculated as an average.

Theoretical spreading rate 7.3 - 11 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Thinner

Jotun Thinner No. 7

Dilution

Maximum 10 %

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Drying times

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Substrate temperature 23 °C

Surface (touch) dry 20 min

Hard dry 40 min

Dry to over coat, minimum 40 min

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Imprimación Multiuso Al Disolvente : 1 Coat

Topcoat

Jotaprof Diamond Brillante or Jotaprof Diamond Mate or Jotaprof Diamond Satinado: 2 Coats

Shelf life at 23 °C

Imprimación Multiuso Al Disolvente 48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.