

## Primax Xtend

### PRODUCT DESCRIPTION

This powder coating product is zinc-free offering to meet standard service requirements for blast-cleaned, phosphated and galvanized steel objects and structures. This product is designed to provide advantage of excellent corrosion protection and inter-coat adhesion properties.

For the combined benefit of corrosion protection with UV exposure and attractive finish, this product can be top coated with suitable exterior durable product offerings from Jotun. The exterior durable product offering from Jotun includes Jotun Facade, Jotun Super Durable, Reveal Era and many more.

The combined coating system of Primax Xtend and Jotun Super Durable is tested at third party test laboratory for corrosion protection for up to CX corrosivity category as per ISO 12944-9.

This product contributes to the Green Buildings Standard credits. Please see section Green Building Standards.

### Application areas

Objects that require enhanced corrosion protection, such as:

- Building structures
- Agricultural machinery
- Electrical enclosures and panels
- Steel fences
- Equipments exposed to coastal environments

### POWDER PROPERTIES

Property	Standard	Result
Specific gravity	Calculated	1.65 ± 0.05 g/cm <sup>3</sup>

### Storage

Keep in a dry cool area. Maximum temperature 25 °C. Maximum relative humidity 60 %. Under these mentioned conditions, product shelf life is 12 months from date of manufacture.

### APPLICATION

#### Pretreatment

The overall quality of the coating system is largely dependent on the type and quality of surface preparation, pretreatment, and the topcoat. Recommended type of surface preparation is grit blasting which must be performed according to specification provided in Jotun's "Application Guide of Powder Coatings on Steel". Grit blasted surfaces are suitable to provide a moderate level of protection. For higher demand, it is recommended to use suitable mechanical and/or chemical surface treatment (e.g. blasting, phosphating). Detailed advice should be sought from the pre-treatment supplier.

For hot dipped galvanized steel, sweep blasting is recommended. Please refer to Jotun's "Application Guide for Jotun Powder Coatings' products on Hot Dipped Galvanized Steel".

#### Chemical pretreatment

Available methods of pretreatment include zinc phosphating and chromating of galvanized steel. Recommended types of pretreatment depend on specific design requirements and on the need for corrosion resistance which is specified in the Performance section of the document.

### Powder application

The system is cured using either full or partial cure regimes for Primax Xtend.

Partial cure of the primer is recommended to enhance inter-coat adhesion between primer and a topcoat following the below schedule.

Curing schedule	Object temperature	Time
Full cure	140 °C	5-15 minutes
	160 °C	<11 minutes
	180 °C	<10 minutes
	200 °C	<10 minutes
Partial cure	140 °C	3-5 minutes*

If primed substrates are partially cured, the application of a topcoat must take place no later than 12 hours at the same site after the application of this product. The shortest possible interval is recommended.

If the primed substrates are fully cured, then they can be temporarily stored for an extended period of time.

In both cases, the primed substrates must be stored away from sunlight, covered with a clean and clear plastic sheet, in a dust-free, cool and dry place.

The inter-coat adhesion properties and the complete system cure must always be verified. When directly fired gas ovens are used, sample of complete system needs to be tested to ensure inter-coat adhesion between the primer and a top coat. For the same reason it is also recommended not to exceed 200 °C oven temperature.

The most suitable partial cure time of the Primax Xtend at temperature selected from the given range is recommended to be defined by a practical experiment. That will help to secure the best decorative and functional performance, considering differences in coated objects and curing ovens.

\*Top coat is then applied and the system should be fully cured in accordance with the recommended curing schedules of either the selected Jotun topcoat or the primer; whichever is more stringent.

Recommended film thickness (µm) : >80

### Equipment

Suitable for Corona or Tribo charging equipment.

## APPEARANCE

**Colour** Only available in light grey colour.

**Gloss** EN ISO 2813 (60°) 75±15

If the significant surface is too small or unsuitable for the gloss to be measured with the glossmeter, the gloss should be compared visually with the reference sample (from the same viewing angle).

## PERFORMANCE

Property	Standard	Result
Adhesion*	EN ISO 2409	Cross-cut rating Gt0 (100 % adhesion)
Impact resistance*	ASTM D2794 (5/8 " ball)	> 60 inch-pounds without film cracking
Cupping test*	EN ISO 1520	Passes 5 mm without film cracking

<b>Resistance to water condensation</b>	ISO 6270-1 ISO 4628-2 ISO 4628-3 ISO 4628-4 ISO 4628-5	Passes or exceeds C4H requirements of ISO 12944-6 ** Passes or exceeds C5VH requirement of ISO 12944-6***
<b>Resistance to neutral salt spray</b>	ISO 9227 ISO 4628-2 ISO 4628-3 ISO 4628-4 ISO 4628-5	Passes or exceeds C4H requirements of ISO 12944-6 ** Passes or exceeds C5VH requirement of ISO 12944-6***
<b>Pull off test</b>	ISO 4624	Passes or exceeds the 2.5 MPa requirement of ISO 12944-6** Passes or exceeds the 2.5 MPa requirement of ISO 12944-6***

\* Typical for this product when applied on zinc-phosphated steel panels (0.8 mm) with coating film thickness 70-90 µm using full cure schedule.

\*\* System 1: Grit blasted (Sa 2½) steel panels, Primax Xtend +Jotun Facade. Total film thickness ~160 µm (primer 80 µm and 60-80 µm topcoat).

\*\*\*System 2: Grit blasted (Sa 2½) zinc phosphated steel panels, Primax Xtend +Jotun Façade 2487. Total film thickness ~160 µm (primer 80 µm and 60-80 µm topcoat).

\*\*\* System 3: Hot dipped galvanized (ISO 1461) steel with sweep blasting, Primax Xtend+Jotun Façade. Total film thickness ~160 µm (primer 80 µm and 60-80 µm topcoat).

For more information on performance using Primax primers and Jotun's various exterior durable topcoats in combination with various methods of surface preparation and various types of substrates can be found on Jotun Primax Performance Matrix brochure.

## Additional information

This product when used in combination of Jotun Facade or Jotun Super Durable, maybe backed by a Product Performance Guarantee when applied to a grit blasted carbon steel substrate. For further advice, please contact your local Jotun office.

## Sustainability

Powder coating is applied in air-and-powder mix in a strictly controlled factory process using electrostatic gun and a high temperature curing oven to create film. Virtually no VOCs are released in the process compared to traditional liquid paints. Unused or oversprayed powder can be recycled with minimal wastage. In addition, all Jotun Powder Coatings' products do not contain intentionally added lead.

## Green Building Standards

This product contributes to Green Building Standard credits by meeting the following specific requirements:

LEED®v4 (2013)

MR credit: Building product disclosure and optimization

- Material Ingredients, Option 2: Material Ingredient Optimization, International Alternative Compliance Path - REACH optimization: Fully inventoried chemical ingredients to 100 ppm and not containing substances on the REACH Authorization list – Annex XIV, the Restriction list – Annex XVII and the SVHC candidate list.  
- Environmental Product Declarations. Product-specific Type III EPD (ISO 14025;21930, EN 15804).

BREEAM® International (2016)

Mat 01: Product-specific Type III EPD (ISO 14025;21930, EN 15804).

The EPDs are available at [www.epd-norge.no](http://www.epd-norge.no)

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.