

Fenomastic Güzel Evim Mineral Şeffaf Koruyucu

Product description

Type

This product is a transparent treatment that retains a natural matt appearance and provides durability.

Recommended use

As a topcoat in areas exposed to high wear and in the event of a risk of water damage.

Product data

Packaging size	0.9 L
Gloss level	3
Generic type	Acrylic emulsion
Solids by volume	30 ± 2 volume%
Specific gravity	1,05
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/f):130 g/l. The product contains max 2 g/l VOC

Application data

Application equipment / methods

Anza roller for smooth substrates.
When using tape, Tesa Sensitive for sensitive surfaces or similar is recommended.

Cleaning of painting tools

Water

Film thickness per coat

Typical recommended range

Dry film thickness 30 - 38 µm

Wet film thickness 100 - 125 µm

Film thickness will vary and is calculated as average.

Theoretical spreading rate 8 - 10 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Water

Dilution

The product is ready to use and should not be thinned.

Conditions during application

Air and surface temperature must be above +10 °C during application.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Substrate temperature

23 °C

Surface (touch) dry

1 h

Dried/cured for immersion

4 weeks

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Topcoat

Fenomastic Güzel Evim Mineral Şeffaf Koruyucu : 1 Coat

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.