

## Lady Design Marmorino Wax

### Product description

#### Type

This product is a water based special wax.

#### Features and benefits

Gives a shiny and polished finish. This product is a special topcoat for Lady Design Marmorino to achieve a smooth and polished design.

#### Recommended use

Ideal for interior surfaces.

#### Substrate

Cement plaster, concrete, block work, rendered surfaces etc.

### Product data

<b>Packaging size</b>	1L
<b>Colours</b>	Clear
<b>Solids by volume</b>	20 ± 2 volume% Theoretical
<b>Specific gravity</b>	0.962
<b>pH value</b>	6.5 to 7.5
<b>VOC comments</b>	21 g/l as per EU Directive 2004/42/EC Theoretical

### Application data

#### Application equipment / methods

Using the spatula, load Marmorino wax on the sponge.  
Gently press and drag the sponge on the Lady Design Marmorino finish, allowing a thin coating of the wax on top of the Marmorino surface. Clean-up the surface of the excessive wax.  
Leave and allow at least 2 hours to dry.  
Perform the final leveling using the stainless steel trowel.

To ensure the desired texture and appearance is achieved, it is required to have a team of skilled applicators or professional painters.

(Important!) Product requires mixing/ stirring prior to every use for easy trowel application. For the 18L pack size, it is recommended to use mechanical agitator before application.

Ensure that Lady Design Marmorino has been allowed to dry for a minimum of 24 hours before applying Lady Design Marmorino Wax.

#### The product can be applied by

Sponge or Spatula or steel trowel.

## Film thickness per coat

### Typical recommended range

Dry film thickness 8 - 10  $\mu\text{m}$

Wet film thickness 40 - 50  $\mu\text{m}$

Film thickness will vary and are calculated as an average.

Theoretical spreading rate 25 - 20  $\text{m}^2/\text{l}$

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

The average consumption can be confirmed at site by a trial application.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

## Thinner

No thinning is required.

## Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

## Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

### The drying time is measured by stated values:

**Relative Humidity (RH) 50 %**

**Substrate temperature** 20 °C

**Surface (touch) dry** 2 h

**Hard dry** 24 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

## Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

This product is available in: United Arab Emirates, Bahrain, Kuwait, Qatar, Oman, Egypt and Libya

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.