

Majestic Nature Parquet Satinado

Product description

Type

Superior Quality interior clear varnish. Based on polyurethane resin.

Features and benefits

Beautiful clear satin finish that respects wood's natural color and texture. Very high UV protection. Does not yellow. Highly resistant to friction, bumps and scratches, and to domestic stains, detergents and water. For interior wooden surfaces such as parquet flooring, stairs and woodwork which require a high protection and durability. European Ecolabel and Euroclases for fire protection Bfl-s1 Certificate.

Recommended use

Ideal for both indoor and outdoor where high quality finished surfaces is required.

Substrate

Wood

Product data

Packaging size	0.75 L and 3 L.
Colours	Transparent
Gloss level	At 60°: 2-5. At 85°: 3-6.
Solids by volume	32 ± 2 volume%
Specific gravity	1.04
VOC	65 g/l ISO 11890 EU

Application data

The product can be applied by

Brush : Recommended.

Roller : Recommended.

Cleaning of painting tools

Water.

Film thickness per coat

Typical recommended range

Dry film thickness	30 - 40 μm
Wet film thickness	106 - 125 μm
	- 8 m ² /l

Thinner

Water

Dilution

No dilution is required.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface must be sanded to achieve maximum adhesion if the application is done after recommended recoating time.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %			
Air temperature	23 °C			
Substrate temperature		10 °C	23 °C	40 °C
Surface (touch) dry		2 h	1 h	30 min.
Hard dry		14 d	7 d	4 d
Dry to over coat, minimum		8 h	4 h	2 h
Dried/cured for immersion	2 weeks			

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Rehabilit Fondo Penetrante : 1 Coat

Topcoat

Majestic Nature Parquet Satinado : 2 Coats

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Majestic Nature Parquet Satinado 48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.