

## Majestic Primer (Wood and Trims)

---

### Product description

#### Type

A premium and environmentally friendly water-based acrylic primer that promotes excellent adhesion on wood substrates without the strong odour of solvent based primer. It is easily sand-able for smooth finishing and provides optimum protection in combination with Majestic Supreme Finish.

#### Features and benefits

Low VOC – Provides better air quality indoors.

Low Odour – Unlike solvent based primer, the paint odour is low during and after application making the property ready for occupancy in shorter period.

Fast Drying – Convenient and quick drying solution that saves times, energy and manpower.

Tannin Blocking – Block wood tannin from penetrating to the topcoat to maintain the beautiful appearance.

Good adhesion – Good wetting property promotes excellent adhesion on wood substrates

Formulated without Harmful Chemicals – Formulates without GHS hazard label, free from harmful chemicals such as APEO, formaldehyde and heavy metals.

#### Recommended use

For interior application, suitable for new and painted substrates.

#### Substrate

On wooden surfaces:

---

### Product data

<b>Packaging size</b>	Packing may vary from country to country according to local requirements.
<b>Colours</b>	White
<b>Solids by volume</b>	39 ± 2 volume%

---

### Application data

#### Remarks

Handle with care. Stir well before use.

#### Application equipment / methods

By brush, roller, or conventional spray.

# Technical Data Sheet

## Majestic Primer (Wood and Trims)



### Spreading rate per coat

**Theoretical** 7.8 m<sup>2</sup>/l - 13 m<sup>2</sup>/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

### Recommended film thickness per coat

**Wet** 77 µm - 128 µm  
**Dry** 30 µm - 50 µm

Film thickness will vary and are calculated as an average.

### Thinner

Water

### Dilution

The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 5%.

### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

#### The drying time is measured by stated values:

**Relative Humidity (RH) 50 %**

<b>Substrate temperature</b>	10 °C	23 °C	40 °C
<b>Surface (touch) dry</b>	4 h	45 min	0.5 h
<b>Hard dry</b>	16 h	4 h	2.5 h
<b>Dry to over coat, minimum</b>	16 h	4 h	2.5 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease etc. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed. It is necessary to employ 2 coats of Majestic Primer (Wood and Trims) before the finish to eliminate tannin stain more effectively. More coats will be needed over rougher surfaces. Water beading on surface due to wax bleed stain should be washed with mineral spirits or hot detergent solutions before primer application.

# Technical Data Sheet

## Majestic Primer (Wood and Trims)



### Recommended paint system

#### Primer

Majestic Primer (Wood and Trims) : 1 Coat

Remark: For dark wood, it is recommended to use 2 coats of primer to achieve good tannin blocking property.

#### Topcoat

Majestic Supreme Finish Gloss : 2 Coats

Majestic Supreme Finish Silky Matt : 2 Coats

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Environmental labelling

### Green Building Standards

The declared product contributes to Green Building Standard credits by meeting the following specific requirements:

LEED®v4 (2013)

- EQ credit: Low emitting materials : VOC content for Wood coatings (275 g/l) (CARB(SCM)2007) and emission <0.5 g/l (CDPH method 1.2 (2017))

- MR credit: Building product disclosure and optimization : Material Ingredients, Option 2: Material Ingredient Optimization, International Alternative Compliance Path - REACH optimization: Fully inventoried chemical ingredients to 100 ppm and not containing substances on the REACH Authorization list – Annex XIV, the Restriction list – Annex XVII and the SVHC candidate list.

BREEAM® International (2016)

- VOC emission exemplary ((ISO 16000-series (2006) or CDPH method 1.2 (2017)) and the VOC content for Interior trim and cladding for wood and metal (90 g/l)

Additional certificates and approvals may be available on request.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.