

Hardtop Metallic Uni

Product description

This is a two component chemically curing aliphatic acrylic polyurethane coating. It is available in a range of metallic finishes with excellent gloss retention. It is an aluminium and micaceous iron oxide (MIO) pigmented product. The product has uniform appearance with good application properties. To be used as topcoat in atmospheric environments.

Typical use

Protective:

Recommended for offshore environments, refineries, power plants, bridges and buildings. Suitable for a wide range of industrial structures.

Colours

selected range of metallic colours

Variations depending on differences in application methods, DFT, temperature, humidity and substrate must be expected.

Technology limitations make exact colour match of metallic finishes not possible.

Product data

| Property | Test/Standard | Description |
|------------------|-------------------|-------------|
| Solids by volume | ISO 3233 | 57 ± 2 % |
| Flash point | ISO 3679 Method 1 | 24 °C |
| Density | calculated | 1.2 kg/l |

| Region | Regulation | Test Standard | VOC Value |
|-----------|---|---------------------|-----------|
| US | CARB(SCM)2020 / SCAQMD rule 1113 | Calculated | 383 g/l |
| Hong Kong | Air Pollution Control (VOC) Regulation | Calculated | 383 g/l |
| EU | European Paint Directive 2004/42/CE | Calculated | 383 g/l |
| EU IED | Industrial Emission Directive 2010/75/EU | Calculated | 383 g/l |
| Korea | Korea Clean Air Conservation Act | Calculated | 383 g/l |
| China | GB 30981-2020 Limit of harmful substances of industrial protective coatings | GB/T 23985-2009 8.3 | 371 g/l |

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Film thickness per coat

Typical recommended specification range

| | | |
|----------------------------|------------|-------------------|
| Dry film thickness | 40 - 60 | µm |
| Wet film thickness | 70 - 105 | µm |
| Theoretical spreading rate | 14.3 - 9.5 | m ² /l |

Surface preparation

Surface preparation summary table

| Substrate | Surface preparation | |
|-----------------|---|---|
| | Minimum | Recommended |
| Coated surfaces | Clean, dry and undamaged compatible coating | Clean, dry and undamaged compatible coating |

Application

Application methods

The product can be applied by

Spray: Use air spray or airless spray.

Varying metallic effects may occur with different application methods or techniques.

Product mixing ratio (by volume)

| | |
|-----------------------------|-----------|
| Hardtop Metallic Uni Comp A | 7 part(s) |
| Hardtop Metallic Uni Comp B | 1 part(s) |

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 10

Thinning ratio may affect the aluminium orientation and brightness.

Guiding data for airless spray

Nozzle tip (inch/1000): 13-19

Pressure at nozzle (minimum): 150 bar/2100 psi

Guiding data for air spray

Nozzle tip: HVLP: 13-15 (inch/1000) / Pressure pot: 1.3-1.5 (mm)

Pressure at nozzle (minimum): HVLP: 2.1 bar/30 psi / Pressure pot: 2.1 bar/30 psi

Deviation in nozzle pressure or thinning ratio may affect the aluminium orientation and brightness.

Drying and Curing time

| Substrate temperature | 5 °C | 10 °C | 23 °C | 40 °C |
|---------------------------|-------|-------|--------|--------|
| Surface (touch) dry | 1.5 h | 1 h | 45 min | 20 min |
| Walk-on-dry | 12 h | 8 h | 4.5 h | 2 h |
| Dry to over coat, minimum | 12 h | 8 h | 4.5 h | 2 h |
| Dried/cured for service | 20 d | 15 d | 7 d | 3 d |

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

| Paint temperature | 23 °C |
|-------------------|-------|
| Pot life | 3 h |

Heat resistance

| | Temperature | |
|------------------|-------------|--------|
| | Continuous | Peak |
| Dry, atmospheric | 120 °C | 140 °C |

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, zinc epoxy, epoxy mastic, polyurethane
Subsequent coat: polyurethane

Packaging (typical)

| | Volume (litres) | Size of containers (litres) |
|-----------------------------|--------------------|--------------------------------|
| Hardtop Metallic Uni Comp A | 17.5 | 20 |
| Hardtop Metallic Uni Comp B | 2.5 | 3 |

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

| | |
|-----------------------------|-------------|
| Hardtop Metallic Uni Comp A | 24 month(s) |
| Hardtop Metallic Uni Comp B | 48 month(s) |

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifouling may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
