

## Fenomastic Wonderwall Life(I)

### Product description

#### Type

This product is a high-quality interior paint based on pure acrylic emulsion with no smell and ultra low VOC.

#### Features and benefits

Comes with luxurious silky finish that gives you the colour you expected along with superior washability keeping your walls beautiful every day. Specially designed with Formaldehyde abatement technology that improves indoor air quality. Specially designed for easy stain removal without affecting the paint properties. Free from harmful chemicals such as APEO, formaldehyde, heavy metals and has low volatile organic compounds (V.O.C.) which ensures good Indoor Quality. Easy to apply and gives a smooth, uniform and beautiful results with good coverage and good hiding property. Also has Anti-Bacterial and Anti-Fungal property.

#### Recommended use

Strongly recommended for interiors of high traffic areas such as kids rooms, Schools, party halls, Kitchens, living rooms, dining rooms etc.

#### Substrate

Cement plaster, concrete, block work, gypsum board etc.

Substrate should have sufficient strength to receive the paint. Any defects in the substrate like surface undulations, cracks, pin holes etc., should be rectified/filled before starting painting. The compatibility of any third party filling material, if used, shall be confirmed with Jotun before application.

### Product data

<b>Packaging size</b>	1 L, 4 L, 10 L and 20 L
<b>Colours</b>	White and Colours available in Jotun Multicolor system.
<b>Solids by volume</b>	38 ± 2 volume%
<b>Specific gravity</b>	1.3 Theoretical only for white colour.

### Application data

#### Remarks

Handle with care. Stir well before use.

#### The product can be applied by

Roller : Recommended.

Spray : Airless spray or Conventional spray.

Brush : Recommended to paint corners and edges.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.021–0.027"
<b>Spray angle degrees</b>	65–80°
<b>Pressure at nozzle</b>	140 - 190 kg/cm <sup>2</sup> (2100 psi)

### Film thickness per coat

#### Typical recommended range

Dry film thickness 20 - 40  $\mu\text{m}$

Wet film thickness 50 - 110  $\mu\text{m}$

Film thickness will vary and are calculated as an average.

Theoretical spreading rate 17 - 14  $\text{m}^2/\text{l}$

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

### Thinner

Water

### Dilution

40 % - 50 %

### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

#### The drying time is measured by stated values:

##### Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	12 h	6 h	2 h
Hard dry	16 h	8 h	4 h
Dry to over coat, minimum	12 h	6 h	2 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

#### Primer

Fenomastic Emulsion Primer : 1 coat

# Technical Data Sheet

## Fenomastic Wonderwall Life(I)



### Filler

Stucco : 2 Coats

and

Fenomastic Emulsion Primer : 1 Coat

### Topcoat

Fenomastic Wonderwall Life(I) : 2 coats

An additional coat may be required for certain bright colours, dark colours and significant colour changes.

### Remarks

Other systems may be specified, depending on area of use.

Masking tape has to be removed immediately after application of the topcoat.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

This product is available in: India

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Certificates

Chemical Emissions Compliance: UL Greenguard Gold Certification as per UL 2818-2013

Formaldehyde Abatement : Purification performance for Formaldehyde as per JC/T 1074-2008

Scrub resistance : Class 1 : EN ISO 11998:2006

Free from heavy metals : ASTM D 3335

Acid & Alkali Resistance : ASTM D 543

Resistance to Household Chemicals : ASTM D 1308

Measurement of antibacterial activity on plastics and other non-porous surfaces as per JIS Z 2801 : 2010

Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber as per ASTM D3273 -16

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

### Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.