

## Hardtop F20 HS

### Product description

This is a two component chemically curing fluoro polymer coating. It has a matt finish with excellent colour retention. To be used as topcoat in atmospheric environments. Fluorine content conforms to the requirement of HG/T 3792-2014 and JT/T 695-2007.

### Typical use

Protective:  
Recommended for refineries, power plants, bridges and buildings. Suitable for a wide range of industrial structures.

### Colors

according to Multicolor Industry tinting system (MCI)

### Product data

Property	Test/Standard	Description	
Solids by volume	ISO 3233	60 ± 2 %	
Gloss level (GU 60 °)	ISO 2813	semi gloss (35-70)	
Flash point	ISO 3679 Method 1	93 °F (34 °C)	
Density	calculated	1.5 kg/l	
Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	3.09 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

Dry film thickness	1.2 mils (30 µm)	4 mils (90 µm)
Wet film thickness	2 mils (50 µm)	6 mils (150 µm)
Theoretical spreading rate	810 ft <sup>2</sup> /gal (20 m <sup>2</sup> /l)	270 ft <sup>2</sup> /gal (6.7 m <sup>2</sup> /l)

Bright colors may need film thickness in the high end of the recommended specification range to achieve opacity.

## Surface preparation

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

## Application

### Application methods

The product can be applied by

- Spray: Use air spray or airless spray.
- Brush: Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Hardtop F20 HS Comp A	10 part(s)
Hardtop F10/F15/F20 HS Comp B	1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 10

### Guiding data for airless spray

Nozzle tip (inch/1000): 13-15  
Pressure at nozzle (minimum): 100 bar/1450 psi

## Drying and Curing time

Substrate temperature	41 °F	50 °F	73 °F	104 °F
Surface (touch) dry	2 h	1 h	30 min	20 min
Walk-on-dry	32 h	16 h	8 h	4 h
Dried to over coat, minimum	32 h	16 h	8 h	4 h
Dried/cured for service	15 d	10 d	5 d	2 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Paint temperature	73 °F
Pot life	5 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	248 °F	284 °F

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, epoxy mastic, polyurethane  
Subsequent coat: fluoro polymer

## Packaging (typical)

	<b>Volume (liters)</b>	<b>Size of containers (liters)</b>
Hardtop F20 HS Comp A	18.2	20
Hardtop F10/F15/F20 HS Comp B	1.8	3

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Shelf life at 73°F (23 °C)

Hardtop F20 HS Comp A 48 month(s)  
Hardtop F10/F15/F20 HS Comp B 48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Caution

This product is for professional use only. The applicator and operator shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators should use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed in the container. Use under well-ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and sought medical attention immediately.

## Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy-based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the data given without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.