

Jotafloor PU VERSA

Product description

This is a two component solvent free, LEED compliant aromatic Polyurethane coating. It an elastomeric coating with superior abrasion, impact, chemical and slip resistance. It can be used an intermediate coat for UV exposed areas , and as a Topcoat for non-exposed areas .

Typical use

Designed for the different levels of the car parks exposed to medium and heavy traffic, mechanical and chemical exposure. Typically recommended for all car park areas such as: ramps, parking bays, drive ways, pedestrian walkways, roof decks.

Approvals and certificates

Determination of Tear Strength - ASTM D 624:2000
Determination of Impact Resistance - ASTM D 2794:93
Determination of Abrasion Resistance - ASTM D 4060:2019
Determination of Chemical Resistance - ASTM 1543:20
Determination of Adhesion Strength - ASTM D 7234:2012
Determination of Crack Bridgeability - ASTM C 1305 M16
Determination of Elongation - ASTM D 412

Additional certificates and approvals may be available on request.

Colours

Available in a wide range of colours.

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	96 ± 2 %
Gloss level (GU 60 °)	ISO 2813	Gloss (70 - 90)
Density	calculated	1.24 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	US EPA Method 24	20 g/l
EU	European Paint Directive 2004/42/CE	Calculated	36 g/l
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	36 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

Minor colour variation may occur with lighter colour shades.

Film thickness per coat

Typical recommended specification range

Dry film thickness	200 - 300	µm
Wet film thickness	208 - 312	µm
Theoretical spreading rate	4.8 - 3.2	m ² /l

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces and Concrete	Clean, dry and undamaged compatible coating as per SSPC SP13/NACE NO 6 /ASTM D4258 -05 /ACI 503.6R-97/SSPC-TR 5/ICRI TECHNICAL GUIDELINE 03741/NACE02203	Clean, dry and undamaged compatible coating as per SSPC SP13/NACE NO 6 /ASTM D4258 -05 /ACI 503.6R-97/SSPC-TR 5/ICRI TECHNICAL GUIDELINE 03741/NACE02203

Laitance deposits are best removed by Planetary diamond disc grinder or by captive blasting followed by vacuum cleaning to remove dust debris. For old concrete, Jotun technical team should visit the site and appropriate surface preparation methodology should be recommended and that is to be followed.

Application

Application methods

The product can be applied by

Roller: Use medium/small pile roller. Care must be taken to achieve the specified dry film thickness. Refer to the Application Guide (AG) for additional information.

Conditions during application :

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

This product should not be applied on to the surfaces which are known to, or likely to suffer from, rising dampness, potential osmosis problems or have a relative humidity greater than 80% as measured in accordance with BS 8203 Appendix A.

A damp proof membrane is essential to prevent rising moisture as it may cause the concrete to become saturated, and negative pressures to adversely affect the bond with Jotafloor product range.

All cementitious substrates should be at least 28 days old and have a moisture content not exceeding 4%.

Product mixing ratio (by volume)

Jotafloor PU VERSA Comp A	3.5 part(s)
Jotafloor PU VERSA Comp B	1 part(s)

NO PART MIXING.

Use a slow speed drill and mixing paddle.

The temperature of the base and curing agent is recommended to be 18 C or higher when the paint is mixed.

Refer to the Application Guide (AG) for additional information.

Thinner/Cleaning solvent

Cleaning solvent : Jotun Thinner No. 10

Thinner not to be used to dilute the product.

Drying and Curing time

Substrate temperature	23 °C	40 °C
Surface (touch) dry	8 h	6 h
Walk-on-dry	24 h	15 h
Dry to over coat, minimum	24 h	15 h
Dry to over coat, maximum, atmospheric	36 h	24 h
Dried/cured for service	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Application in external areas & above 40 C consult with Jotun representative for guidance.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dry to over coat, maximum, atmospheric: The longest time allowed before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature **23 °C**

Induction time	2 min
Pot life	20 min

Product compatibility

Previous coat: Jotafloor Sealer HS or Jotafloor SF PR 150 or Jotafloor PU VERSA

Subsequent coat: Jotafloor PU Topcoat or Jotafloor PU Ultra

In case Jotafloor Sealer HS is used, multiple coats are recommended. Contact your local Jotun office for guidance.

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotafloor PU VERSA Comp A	7.8	10
Jotafloor PU VERSA Comp B	2.2	3

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Jotafloor PU VERSA Comp B should be stored between 10°C to 35°C as it tends to crystallise when stored below 10°C.

Shelf life at 23 °C

Jotafloor PU VERSA Comp A	12 month(s)
Jotafloor PU VERSA Comp B	12 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.