

Jotachar JF750 XT

Product description

This is a two component solvent free amine cured 100% solids epoxy intumescent coating. Specially designed as an intumescent coating to provide fire protection for steel in hydrocarbon pool and jet fires for different types of structures and equipment. No additional reinforcing mesh is required. To be used as mid coat as part of a complete system in atmospheric environments. Suitable on approved primers on carbon steel, aluminum, hot dipped galvanized steel and stainless steel substrates, subject to certification.

Typical use

Typically used in the oil, gas and energy industries. Suitable in both offshore and onshore environments for the passive fire protection of structural carbon steel, stainless steel, GRP and concrete, subject to certification. Designed for exposure in a wide range of ambient temperatures down to -52°C. Jotachar JF750 XT is suitable for use on process pipe work, vessels or equipment operating up to 95 °C. At higher service temperatures, Jotatherm TB550 should be used as thermal syntactic insulation between substrate and Jotachar or as thermal insulation on top of Jotachar for atmospheric heat radiation. Please contact your local sales representative for more information.

Approvals and certificates

BS 476 Part 21 Hydrocarbon Pool Fire curve for structural and divisional fire protection
ISO 22899 Jet Fire Standard for structural and divisional fire protection
Pre-qualified in accordance with NORSOK M-501 in selected systems
Certified and approved by Lloyds Register of Shipping
Det Norske Veritas Type Approval
ANSI/UL 1709 5th edition: Rapid Rise Fire Tests of Protection Materials for Structural Steel
UL 2431: Safety Durability of Fire Resistive Coatings and Materials

Additional certificates and approvals may be available on request.

Colors

grey

Product data

Property	Test/Standard	Description	
Solids by volume	ISO 3233	100 %	
Flash point	ISO 3679 Method 1	212 °F (100 °C)	
Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	US EPA Method 24	0.04 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.

Applied density by plural component spray (ISO 1183:1987 Method A): $1.0 \pm 0.1 \text{ g/cm}^3$

Note: Applied density value is typical and provided for guidance only. The final applied density will be affected by equipment setup and/or method of application. Please refer to the Application Guide for this product.

Film thickness per coat

Typical recommended specification range

Dry film thickness:

1 - 27 mm (dependent upon the fire case and project specific requirements)

Theoretical spreading rate:

1 kg of Jotachar JF750 XT will cover 1 m^2 per 1 mm applied (based on plural component spray)

Typical first coat thickness achievable is 6 mm.

Subsequent coats of up to 8mm can be applied.

High film build can be achieved dependent upon steelwork configuration, geometry, ambient conditions, pump type and set up as well as primer used.

Maximum WFT is the thickness at which the system can be applied without sagging or slumping.

Surface preparation

Refer to the Application Guide (AG) for additional information.

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Application

Application methods

The product can be applied by

Spray: Use two component heated plural spray unit or modified airless spray (with heating equipment). Refer to the Application Guide (AG) for additional information.

Note: All pumps used for the application of this product must be certified by Jotun.

Trowel: Refer to the Application Guide (AG) for additional information.

Product mixing ratio (by weight)

Jotachar JF750 XT Comp A 1 part(s)
Jotachar JF750 XT Comp B 1 part(s)

Individual components must have been stored for minimum 12 hours at 20 to 25 °C (68-77 °F). Stir/mix thoroughly with a power agitator before application.

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 7 / Jotun Thinner No. 10 / Jotun Thinner No. 17

Thinning max: 5 %

Thinning is typically 3 % by volume for modified airless spray and manual application.
For rolling, use Jotun Thinner No. 7, Jotun Thinner No. 10 or Jotun Thinner No. 17.

Note: Korean VOC regulation "Korea Clean Air Conservation Act" and its corresponding thinning limit will prevail over recommended thinning volumes.

Cleaning solvent: Jotun Thinner No. 17

When thinners are used as a cleaning solvent, the use must be in accordance with prevailing local regulations.

Guiding data for airless spray

Nozzle tip (inch/1000): 31-41
Pressure at nozzle (minimum): 200 bar/2900 psi

Drying and Curing time

Substrate temperature	41 °F	59 °F	73 °F	104 °F
Surface (touch) dry	8 h	6 h	4 h	3 h
Walk-on-dry	48 h	17 h	12 h	5 h
Dried to over coat, minimum	8 h	5 h	3 h	2 h
Dried/cured for service	48 h	24 h	16 h	12 h

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Dry to overcoat minimum is with self. See additional guidance for Topcoating.

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Topcoating:

The system should be dry to handle and coating thickness gauge should not leave an indentation on the coating. Prior to application of topcoat, the applicator must ensure that the specified dry film thickness has been achieved.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature

59 °F 73 °F

Pot life

70 min 60 min

The given figures are for trowel and roller workability.

Working pot life is not applicable for plural airless spray application as the material is mixed at the spray gun during application. For single leg airless spray and manual application, mixed material should be applied with minimum delay. Due to exothermic reaction, the larger the volume of mixed material, the shorter the pot life will be.

Heat resistance

Dry, atmospheric

Continuous: 95 °C

Can be specified from 95°C to 150°C with Jotatherm TB550 as a heat reduction layer. Subject to technical review, please contact Jotun.

Jotatherm TB550 can be used as thermal insulation on top of Jotachar for atmospheric heat radiation. Aesthetic properties may suffer at higher temperatures.

Above 150°C, alternative insulation arrangements will be required.

Please contact your local sales representative for more information.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, zinc epoxy, epoxy zinc phosphate, epoxy mastic

Subsequent coat: crosslinked acrylic, polyurethane, polysiloxane, epoxy

Primers used under this product must be approved by Jotun. For the list of approved primers, please consult Jotun.

See Application Guide.

Packaging (typical)

	Weight	Size of containers (liters)
Jotachar JF750 XT Comp A	20 kg / 10 kg	20 / 10

Jotachar JF750 XT Comp B

20 kg / 10 kg

20 / 10

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Storage temperature not to exceed 95 °F (35 °C). Store away from direct sunlight. Protect from frost.

Shelf life at 73°F (23 °C)

Jotachar JF750 XT Comp A 18 month(s)

Jotachar JF750 XT Comp B 18 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

Technical Data Sheet

Jotachar JF750 XT



The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.