

## Jotatop Pro

### Product description

This is a two component acrylic coating. The product does not contain isocyanates, neither does it generate di-isocyanates during hotwork / welding or fire. It has a glossy finish with good color and gloss retention. It is a high solids product. The product has good application properties with low dry spray. To be used as topcoat in atmospheric environments.

### Typical use

Protective:

Recommended for offshore environments, refineries, power plants, bridges and buildings. Suitable for a wide range of industrial structures. Used as a topcoat in pre-qualified NORSOK systems.

Marine:

Recommended for topside, deck and superstructure.

### Approvals and certificates

Approved to meet the requirements of Network Rail and UK Highway Agency Item 167 for use on bridges and highway infrastructure.

Additional certificates and approvals may be available on request.

### Colors

according to color card and Multicolor Industry tinting system (MCI)

### Product data

Property	Test/Standard	Description
Solids by volume		60 ± 2 %
Gloss level (GU 60 °)	ISO 2813	70-85
Flash point	ISO 3679 Method 1	82 °F (28 °C)
Density	calculated	1.3 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	2.94 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.  
Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

Dry film thickness	2 mils (50 µm)	5 mils (125 µm)
Wet film thickness	3 mils (85 µm)	8 mils (210 µm)
Theoretical spreading rate	490 ft <sup>2</sup> /gal (12 m <sup>2</sup> /l)	200 ft <sup>2</sup> /gal (4.8 m <sup>2</sup> /l)

Bright colors may need film thickness in the high end of the recommended specification range to achieve opacity.

## Surface preparation

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

## Application

### Application methods

The product can be applied by

Spray:	Airless or Conventional (Conventional may be used for small areas)
Brush:	Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
Roller:	May be used for small areas. Care must be taken to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Jotatop Pro Comp A	5 part(s)
Jotatop Pro Comp B	1 part(s)

The coating shall be mixed with an air powered mechanical paint mixing tool that is clean and fit for purpose. Mix complete units only.

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 10

Please consult the local Jotun representative for advice during application in severe conditions. Do not thin more than allowed by local Health, Safety and Environment Regulations.

### Guiding data for airless spray

Nozzle tip (inch/1000):	13-19
Pressure at nozzle (minimum):	150 bar/2100 psi

## Drying and Curing time

Substrate temperature	41 °F	50 °F	73 °F	104 °F
Surface (touch) dry	2.5 h	2 h	1 h	1 h
Walk-on-dry	25 h	22 h	10 h	3.5 h
Dried to over coat, minimum	25 h	22 h	10 h	3.5 h
Dried/cured for service	15 d	10 d	7 d	3 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Paint temperature	73 °F
Pot life	4 h

The temperature of base and curing agent is recommended to be 18 °C or higher when the product is mixed.

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Product compatibility

Previous coat: epoxy, epoxy mastic, two component acrylic

Subsequent coat: two component acrylic

## Packaging (typical)

	Volume (liters)	Size of containers (liters)
Jotatop Pro Comp A	4.2/16.7	5/20
Jotatop Pro Comp B	0.8/3.3	1/5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### Shelf life at 73°F (23 °C)

Jotatop Pro Comp A	24 month(s)
Jotatop Pro Comp B	12 month(s)

Jotatop Pro delivered in custom packaging has half of the shelf life stated above.

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Environmental Documentation

This product can contribute to Green Building Standard credits. Please refer to [Jotun.com](http://Jotun.com) for more information or contact your local Jotun representative.

Environmental Product Declaration (EPD) is available at [www.epd-norge.no](http://www.epd-norge.no)

## Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.