

## Guard Insulate HB

### PRODUCT DESCRIPTION

Guard Insulate HB is a series of insulating powder coatings with edge coverage properties specially designed to meet stringent requirements of EV battery, energy storage industries and other applied electrical industries that requires high electrical insulation properties. It provides safe and reliable solution with electrical insulation resistance, voltage resistance, heat resistance and moisture resistance properties.

### Application areas

Typical application areas:

Busbar

Fixed rotor

Capacitor

Other equipment parts with insulation and edge coating requirements

### POWDER PROPERTIES

Property	Standard	Result
Specific gravity	Calculated	Typically $1.6 \pm 0.2 \text{ g/cm}^3$

### Storage

Keep in a dry cool area. Maximum temperature 25 °C. Maximum relative humidity 60 %. If stored longer than 6 months a quality test must be performed.

### APPLICATION

#### Pretreatment

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the pretreatment. For optimal results, it is recommended to follow the pretreatment supplier's instructions and recommendations.

#### Powder application

Curing schedule	Object temperature	Time
Guard Insulate HB	200 °C	10 minutes

Other curing schedules can be created upon technical approval.

Recommended film thickness ( $\mu\text{m}$ ):  $\geq 300$

#### Equipment

Suitable for Corona or Tribo charging equipment and dipping application.

## APPEARANCE

**Colour** The product is available in a wide assortment of custom-made colours, including RAL and NCS.

**Gloss** ISO 2813 (60°) 60-100

**Finish** Smooth

If the significant surface is too small or unsuitable for the gloss to be measured with the glossmeter, the gloss should be compared visually with the reference sample (from the same viewing angle).

Other gloss levels are available upon technical approval.

## PERFORMANCE

The technical data provided below are typical for this product when applied as follows:

Substrate Chrome-free aluminum panels

Substrate thickness (mm) 0.8 mm

Film thickness (µm) 150-200

Typical values when tested.

Property	Standard	Result
<b>Adhesion</b>	ASTM D3359	Cross-cut adhesion rating 5A
<b>Film hardness</b>	ASTM D3363 Gauge Gouge Test modified (Derwent Graphic) GB/T 6739 Modified	≥HB (No damage of film)
<b>Dielectric strength</b>	IEC 60243-1 GB/T 1408.1	> 40 kV/mm
<b>Surface resistivity</b>	IEC 62631-3-2	>10 <sup>14</sup> ps (Ω/sq)
<b>Volume resistivity</b>	IEC 62631-3-1	>10 <sup>15</sup> pv (Ω·cm)
<b>Insulation resistance</b>	Internal Method (DC 1000V, 60s)	>1 GΩ
<b>Voltage resistance</b>	Internal Method (DC 5000V, 60s)	Leakage current <1 mA
<b>Insulation after abrasion resistance</b>	ISO 7784-2 ASTM D4060 GB/T 1768 CS-17 wheels, 1000 grams load, 3000 cycles	Meet the requirements of insulation and voltage resistance after abrasion test
<b>Cyclic temperature and humidity test</b>	GB 38031 (55 °C, 6 cycles)	No blistering, no cracking, no peeling off and no loss of adhesion.. Meet the requirements of insulation and voltage resistance after test.
<b>High temperature resistance</b>	ISO 3248 GB/T 1735 (130 °C, 1000 Hrs)	No blistering, no cracking, no peeling off and no loss of adhesion.. Meet the requirements of insulation and voltage resistance after test.
<b>Cyclic temperature test</b>	ISO 6469-1 Modified GB 38031 Modified (-40°C~85°C, 1000 cycles)	No blistering, no cracking, no peeling off and no loss of adhesion.. Meet the requirements of insulation and voltage resistance after test.
<b>Acid and Alkaline resistance</b>	ISO 2812-1 GB/T 9274 (5% HCl-2Hrs & 5% NaOH-2 Hrs)	No blistering, no cracking, no peeling off and no loss of adhesion.. Meet the requirements of insulation and voltage resistance after test.

<b>Water resistance</b>	ISO 2812-2 GB/T 1733 (25°C, 168Hrs)	No blistering, no cracking, no peeling off and no loss of adhesion. Meet the requirements of insulation and voltage resistance after test.
<b>Flame retardancy</b>	UL 94	Rating V-0
<b>Prohibited substances</b>	RoHS ELV REACH	Meet all requirements
<b>Hydrothermal ageing</b>	IEC 60068-2-67 GB/T 2423.50 (85°C and 85% RH for 1000 hours)	No blistering, no cracking, no peeling off and no loss of adhesion.
<b>Edge coverage</b>	ASTM D2967 Modified (Customized test sample with pre-treatment)	65%

### Sustainability

Powder coating is applied in air-and-powder mix in a strictly controlled factory process using electrostatic gun and a high temperature curing oven to create film. Virtually no VOCs are released in the process compared to traditional liquid paints. Unused or oversprayed powder can be recycled with minimal wastage. In addition, all Jotun Powder Coatings' products do not contain intentionally added lead.

### Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.