

Muki CZ

Product description

This is a two component inorganic ceramic medium zinc ethyl silicate coating. It is a shop primer designed for high welding and cutting speed, giving reduced weld porosity and back burning. It is fast drying and has good abrasion resistance making it suitable for stacking shortly after application. Can be used as temporary primer in a new construction phase or as primer in a complete coating system in atmospheric and immersed environments. May be used as a single coat system. Designed for temperatures up to 800 °C providing excellent resistance to damage caused by welding (backburning) and cutting. Suitable for properly prepared carbon steel substrates and recommended to be applied in an automated shop priming line. Compatible with advanced welding technologies including MIG, MAG and G-FCAW.

Typical use

Recommended for structural steel including marine, offshore environments and refineries. Specially suited as primer for areas with high risk of back burning during construction phase.

Colours

dark grey

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	28 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	14 °C
Density	calculated	1.5 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	650 g/l
Hong Kong	Air Pollution Control (VOC) Regulation	Calculated	650 g/l
EU	European Paint Directive 2004/42/CE	Calculated	624 g/l
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	624 g/l
Korea	Korea Clean Air Conservation Act	KS M ISO 11890-1	662 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	15 - 35	µm
Wet film thickness	55 - 125	µm
Theoretical spreading rate	18.7 - 8	m ² /l

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1)	Sa 2½ (ISO 8501-1)

St 2 is applicable for the reverse side of welding areas, and on inside walls under insulation.

Application

Application methods

The product can be applied by

Spray:	Use air spray or airless spray.
Brush:	Recommended for touch-up purposes.

Product mixing ratio (by volume)

Muki CZ Comp A	10 part(s)
Muki CZ Comp B	6 part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 4 / Jotun Thinner No. 25

Jotun Thinner No. 4: for fast evaporation
Jotun Thinner No. 25: for slow evaporation

Jotun Thinner No. 28 can be used as alternative to Jotun Thinner No. 4 for fast evaporation.
Jotun Thinner No. 17 can be used as alternative cleaning solvent.

Guiding data for airless spray

Nozzle tip (inch/1000):	15-23
Pressure at nozzle (minimum):	50 bar/700 psi

Drying and Curing time

Substrate temperature	23 °C	40 °C
Surface (touch) dry	1 min	20 sec
Walk-on-dry	3 min	1 min
Dry to over coat, minimum	2 d	1 d
Dried/cured for service	2 d	1 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Pot life	24 h

Heat resistance

Dry, atmospheric:
Continuous: 400 °C Peak: 800 °C

Immersed, sea water:
Continuous: 50 °C Peak: 50 °C

Designed for temperatures up to 800 °C providing excellent resistance to damage caused by welding (backburning) and cutting.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Subsequent coat: epoxy, alkyd, acrylic, epoxy mastic, zinc epoxy

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Muki CZ Comp A	10	10
Muki CZ Comp B	6	20

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Muki CZ Comp A	6 month(s)
Muki CZ Comp B	24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
